

# Ultrafast third-order optical nonlinearity of several sandwich-type phthalocyaninato and porphyrinato europium complexes\*

Huang Wen-Tao(黄文涛)<sup>a)</sup>, Li Yan(李 焱)<sup>a)†</sup>, Xiang Hong(向 红)<sup>a)</sup>,  
Yang Hong(杨 宏)<sup>a)</sup>, Gong Qi-Huang(龚旗煌)<sup>a)‡</sup>, Huang Yan-Yi(黄岩谊)<sup>b)</sup>,  
Huang Chun-Hui(黄春辉)<sup>b)</sup>, and Jiang Jian-Zhuang(姜建壮)<sup>c)</sup>

<sup>a)</sup>State Key Laboratory for Mesoscopic Physics and Department of Physics, Peking University, Beijing 100871, China

<sup>b)</sup>State Key Laboratory of Rare Earth Material Chemistry and Application, College of Chemistry, Peking University, Beijing 100871, China

<sup>c)</sup>Department of Chemistry, Shandong University, Jinan 250100, China

(Received 4 March 2005; revised manuscript received 11 April 2005)

The third-order optical nonlinearity of two sandwich-type phthalocyaninato and porphyrinato europium complexes, including double- and triple-deckers ( $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$ ,  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ ,  $\text{Pc}$ =phthalocyanine,  $\text{TPP}$ =5, 10, 15, 20-tetraphenylporphyrinate), was investigated by using the femtosecond time-resolved optical Kerr gate method at 830 nm wavelength. Their second-order hyperpolarizability is estimated to be  $0.74 \times 10^{-30}$  esu and  $3.0 \times 10^{-30}$  esu respectively. This exhibits an evident enhancement in comparison with  $0.47 \times 10^{-30}$  esu for one-decker  $\text{Eu}(\text{Pc})(\text{acac})$  ( $\text{acac}$ =acetylacetonate), which is also measured under the same conditions. The enhancement is attributed to the introduction of lanthanide metal to the large  $\pi$ -conjugated system, intermacrocycle interaction and two-photon resonance etc.

**Keywords:** ultrafast third-order optical nonlinearity, phthalocyanine, porphyrin

**PACC:** 4265, 4280W, 7820, 7855K

## 1. Introduction

Phthalocyanines and porphyrins are two classes of stable, robust and functional tetrapyrrole derivatives. They are well-known macrocyclic compounds with highly delocalized large  $\pi$ -electron system which endows them unique properties useful for catalysis, medicine, photovoltaic cells etc.<sup>[1–3]</sup> In addition, their capability of including many metallic ions makes them typical organometallic compounds with effective charge-transfer transitions between metal atom and ligand. Such metal-ligand bonding displays large molecular hyperpolarizability, which was caused by the transfer of electron density between the metal atom and the conjugated macrocycle. So they are considered to be promising candidates as usable nonlinear optical (NLO) materials with large third-order optical

nonlinearity.<sup>[4–9]</sup> The diversity of central metal atoms and peripheral substituents offers ease of synthesizing and tailoring. Furthermore, three-dimensional structures can be formed by polymerization or by coordination of transition metals. The unique sandwich-type cofacial stack extending of their planar  $\pi$ -electron systems such as  $\text{MPc}_2$  attracts great attention by introducing particularly intermacrocycle interaction.<sup>[10–15]</sup>

For instance, sandwich-type bis (phthalocyaninato or porphyrinato) metal complexes have been investigated as promising electrochromic display materials and optical limiting materials.<sup>[16–18]</sup> Also considered as potential third-order NLO materials, several lanthanide bis (phthalocyanines) and their anions have been systematically investigated years ago.<sup>[10]</sup> Their second-order hyperpolarizability ( $\gamma$ ) enhanced more than 2 orders of magnitude comparing with  $\gamma$

\*Project supported by the National Key Research Program of China (Grant No TG1999075209) and the National Natural Science Foundation of China (Grant Nos 10434020, 90206003 and 60378012).

†E-mail: li@pku.edu.cn

‡Corresponding author. E-mail: qhgong@pku.edu.cn

of metal-free monophthalocyanine. And a strong enhancement of  $\gamma$  with oligomer size  $n$  scaling as  $n^3$  ( $n = 1 - 3$ ) has been found when the  $\gamma$  of  $\mu$ -oxo silicon phthalocyanine oligomers ( $\text{SiPcO}$ ) $_n$  is studied.<sup>[11]</sup> Such unique cofacial stack extending of planar  $\pi$ -electron systems was considered models for studying structure relationships of third-order NLO property, particularly intermacrocycle interaction. Manas *et al* have theoretically analysed the effects of cofacial stack on  $\gamma$ , and suggested the experimental investigation on the third-order NLO property of triple-decker sandwich-type metallophthalocyanine.<sup>[19]</sup>


We have previously reported the measurement of the second-order hyperpolarizability of two triple-decker mixed phthalocyaninato and porphyrinato Sm complexes,  $\text{Sm}_2(\text{Pc})_2(\text{TPP})$  and  $\text{Sm}_2(\text{Pc})(\text{TPP})_2$ .<sup>[20]</sup> In this paper we studied the third-order NLO property of three samples with the same metallic ions by using femtosecond time-resolved optical Kerr gate method at 830 nm wavelength, including a heteroleptic triple-decker  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ , a double-decker  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$  and a one-decker  $\text{Eu}(\text{Pc})(\text{acac})$ . Their second-order hyperpolarizabilities were esti-

mated to be  $3.0 \times 10^{-30} \text{esu}$ ,  $0.74 \times 10^{-30} \text{esu}$  and  $0.47 \times 10^{-30} \text{esu}$  respectively.

## 2. Experiments

### 2.1. Materials

The  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ ,  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$  and  $\text{Eu}(\text{Pc})(\text{acac})$  were synthesized by Jiang *et al*, and the detail process was reported elsewhere.<sup>[21,22]</sup> Their molecular structures have been confirmed by the  $^1\text{H}$  NMR spectra, and many similar double- and triple-decker compounds with varied metallic ions have been synthesized and studied by the  $^1\text{H}$  NMR spectra, mass spectra, IR and resonance Raman spectra, electronic spectra etc.<sup>[23,24]</sup> We present a schematic picture of the structure of  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$  and  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$  in Fig.1.  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$  was concluded as  $(\text{TPP}) \text{Eu} (\text{Pc}) \text{Eu} (\text{TPP})$  with the original planar  $\text{Pc}/\text{TPP}$  ring rotated around the axis determined by two metallic atoms and slightly curved because of the strong intermacrocycle interaction.<sup>[21,25,26]</sup>



**Fig.1.** A schematic picture of the molecular structures of  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$  (left) and  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$  (right) ( $\text{R}=\text{OC}_5\text{H}_{11}$ ).


## 2.2. Experimental setup

The standard optical Kerr gate method was employed to study the ultrafast NLO response of sample solutions at 830nm, with the femtosecond laser pulses generated from a Ti:sapphire oscillator (Mira 900F, Coherent, USA). Detailed apparatus configuration has been described in our previous reports.<sup>[27–29]</sup> In brief, the laser output pulse was split into a strong pump and a weak probe pulse train with a ratio of 10:1 and 45° polarization difference. Two beams were carefully adjusted parallel and focused by a convex lens to overlap spatially in the sample solution filled in a 1mm-thickness glass cell. After the interaction, with the pump beam blocked, the probe beam was collimated into an analyser (polarizer) whose transmission axis was strictly perpendicular to its original polarization. Only the generated orthogonal signal and optical Kerr effect (OKE) signal passed and were detected by a photodiode after the analyser. A motor-driven optical delay line was used in the optical path of the pump beam to obtain time-resolved signal. In order to obtain good signal/noise ratio, the pump and probe beams were chopped at different frequencies and the signal was amplified at the sum frequency by a lock-in amplifier (SR830, Stanford, USA). A computer was used to control the step motor and monitor the measurement. By replacing the sample cell with a 0.3mm-thick BBO crystal, we can determine the zero delay point and obtain the autocorrelation signal of the system. We got 120fs for the full width at half-maximum of the laser pulses at 830nm.

## 3. Results and discussion

The linear absorption spectra of our sample solutions ( $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ ,  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$  and  $\text{Eu}(\text{Pc})(\text{acac})$ ) in chloroform were shown in Fig.2, which were measured by Agilent 8453 UV-visible spectroscopy system. The solutions were contained in a 1mm-path-length cuvette with concentrations of  $4.6 \times 10^{-5}\text{M}$  for  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ ,  $7.0 \times 10^{-5}\text{M}$  for  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$  and  $23.3 \times 10^{-5}\text{M}$  for  $\text{Eu}(\text{Pc})(\text{acac})$ . The absorptions at ca 350 and 680 nm can be attributed to the B bands and Q bands of Pc rings respectively. The former is clear for all three solutions, but the latter totally disappears or shifts for  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ , which indicates strong intermacrocycle interaction. For  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ , the absorption ca 420 nm can be attributed to the B bands of TPP ring, and its relative intensity to the peak ca 350 is 2:1 cor-

responding to the TPP: Pc ratio in this complex.<sup>[21]</sup> The absorptions at 830 nm can be neglected for all samples.




**Fig.2.** Absorption spectra of  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ ,  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$  and  $\text{Eu}(\text{Pc})(\text{acac})$  in chloroform from 300 nm to 1000 nm.

We followed the standard reference measurement to obtain the third-order NLO susceptibility  $\chi^{(3)}$  of a sample solution.<sup>[27–30]</sup> The following equation

$$\chi_S^{(3)} = \chi_R^{(3)} \left( \frac{I_S}{I_R} \right)^{1/2} \left( \frac{n_S}{n_R} \right)^2 f(\alpha) \quad (1)$$

is used to calculate  $\chi^{(3)}$ . The subscripts, S and R, represent the parameters of the sample solution and the reference  $\text{CS}_2$  respectively.  $I$  is the intensity of the obtained OKE signal.  $n$  is the refractive index.  $f(\alpha)$  is an absorption correction factor, which equals one when the corresponding absorption can be neglected. The  $n$  of  $\text{CS}_2$  is 1.62 and its  $\chi^{(3)}$  was estimated to be  $1.0 \times 10^{-13}$  esu in femtosecond time scale.<sup>[31]</sup> We can use the  $n$  of chloroform at 20°C ( $n = 1.446$ ) as the refractive index of the solution since the concentration of sample is very dilute.

The typical OKE response of  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$  in chloroform is shown in Fig.3. We measured the signal of the pure solvent under the same condition, which was very small and subtracted in calculation. We also measured the signal of the pure  $\text{CS}_2$  under identical condition for comparison. According to Eq.(1), the third-order NLO susceptibility for the solution of  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$  at  $4.6 \times 10^{-5}\text{M}$  is deduced to be  $2.8 \times 10^{-13}$  esu. From the figure, we notice that the NLO response of the solution is the same time scale as the pulse duration and no decay process appeared. It is believed that such an instantaneous response in femtosecond time scale can be predominantly attributed to the delocalization of electrons.<sup>[32]</sup>




**Fig.3.** The optical Kerr effect response of the solution of  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$  dissolved in chloroform at concentrations of  $4.6 \times 10^{-5} \text{M}$ ,  $3.1 \times 10^{-5} \text{M}$  and  $2.0 \times 10^{-5} \text{M}$ .

In order to verify the linear dependence of the measured  $\chi^{(3)}$  on the solution concentration, the OKE signals of the sample at different concentrations have been measured. We give the data in Fig.4 with  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$  as a representative. The linear fit of the three values of  $\chi^{(3)}$  ( $2.8 \times 10^{-13} \text{esu}$ ,  $1.9 \times 10^{-13} \text{esu}$ , and  $1.3 \times 10^{-13} \text{esu}$ ) on the concentrations ( $4.6 \times 10^{-5} \text{M}$ ,  $3.1 \times 10^{-5} \text{M}$  and  $2.0 \times 10^{-5} \text{M}$ ) is excellent. The fitted line is very close to origin. It concludes that our experimental measurement is reliable and the followed equation,

$$\gamma = \chi^{(3)}/NL, \quad (2)$$

can be introduced to estimate the second-order hyperpolarizability ( $\gamma$ ) of the sample molecule. Here  $N$  is the number density of the sample molecule and  $L$  is the local field correction factor given by  $[(n^2+2)/3]^4$ . The calculated  $\gamma$  is  $3.0 \times 10^{-30} \text{esu}$  for  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ . And the  $\gamma$  of  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$  and  $\text{Eu}(\text{Pc})(\text{acac})_2$  are deduced to be  $0.74 \times 10^{-30} \text{esu}$  and  $0.47 \times 10^{-30} \text{esu}$  by the same routine respectively.



**Fig.4.** Linear concentration dependence of the third-order NLO susceptibility  $\chi^{(3)}$  of  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$  in chloroform.

In our previous letter, we have suggested that the acceptable non-resonance  $\gamma$  for metal-free Pc and tetraphenylporphyrin is about  $10^{-33} \text{esu}$  at 830 nm.<sup>[20]</sup> Although the differences of measurement systems and experimental conditions have made the measured susceptibilities hard to be compared with each other, it is obvious that the third-order optical nonlinearity of our complexes is strongly enhanced with 2–3 orders relative to the mono-layer metal-free Pc and TPP. We have previously reported the large second-order hyperpolarizability of triple-decker mixed phthalocyaninato and porphyrinato Sm complexes  $\text{Sm}_2(\text{Pc})_2(\text{TPP})$  and  $\text{Sm}_2(\text{Pc})(\text{TPP})_2$ , which are  $2.6 \times 10^{-30} \text{esu}$  and  $2.2 \times 10^{-30} \text{esu}$ . Introducing of Lanthanide metal to the large  $\pi$ -conjugated system, we have concluded that intermacrocycle interaction and two-photon resonance are responsible for their large optical nonlinearity.<sup>[20]</sup> And these three factors also lead to the strong enhancement for  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ . The measured  $\gamma$  of  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$  is about 4 times as that of  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$ . Two-photon resonance is considered responsible for this enhancement based on the theoretical analysis of Manas *et al.*<sup>[19]</sup> They suggested a fourfold enhancement of the  $\gamma$  of  $(\text{SiPcO})_3$  trimer to  $(\text{SiPcO})_2$  dimer due to two-photon resonance. In absorption spectra of  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ , it shows evidence for two-photon resonance that the B band of TTP locates near 415 nm (the double-frequency wavelength of 830 nm). The measured  $\gamma$  of  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$  is appreciably larger than other results for bis(phthalocyanines) which ranged between  $0.10 \times 10^{-30} \text{esu}$  and  $0.50 \times 10^{-30} \text{esu}$ .<sup>[10,15]</sup> Shirk *et al* gave  $0.22 \times 10^{-30} \text{esu}$  for  $\text{Eu}(\text{Pc})_2$  at 1064 nm by degenerated four-wave mixing. Such difference may come from the wavelength dispersion of  $\gamma$  and the influence of peripheral substituent. According to previous work on bis(phthalocyanines), introducing Lanthanide Eu and strong intermacrocycle interaction are responsible for the large nonlinearity of  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$ . The measured  $\gamma$  of  $\text{Eu}(\text{Pc})(\text{acac})$  is about 10 times as those for metalophthalocyanines with normal metals.<sup>[4,33]</sup> Despite the especial uncomplete f-shell of Lanthanide Eu, out planar position of Eu and acaca may be helpful in such enhancement. Nalwa *et al* have found a fourfold enhancement of nonlinearity for  $\text{VOPc}(\text{NH}_2)_4$  to  $\text{CuPc}(\text{NH}_2)_4$  and introduced the effect of such structure.<sup>[34]</sup> The  $\gamma$  of  $\text{MoOPc}$  was measured as  $0.31 \times 10^{-30} \text{esu}$ , which is close to our result.<sup>[15]</sup>

## 4. Conclusion

In summary, the third-order optical nonlinearities of a triple-decker mixed porphyrinato-phthalocyaninato Lanthanide compound  $\text{Eu}_2(\text{Pc})(\text{TPP})_2$ , a double-decker  $\text{Eu}[\text{Pc}(\text{OC}_5\text{H}_{11})_8]_2$  and a mono-layer  $\text{Eu}(\text{Pc})(\text{acac})$  were explored by using femtosecond optical Kerr gate method. Their instantaneous second-order hyperpolarizabilities were

estimated to be  $3.0 \times 10^{-30} \text{esu}$ ,  $0.74 \times 10^{-30} \text{esu}$  and  $0.47 \times 10^{-30} \text{esu}$  respectively. Mechanism for such large nonlinearity was discussed.

## Acknowledgments

The authors are grateful to Professor Liu Chun-Ling for her assistant in the absorption spectroscopy measurement.

## References

- [1] Sheldon R A (Ed.) 1994 *Metalloporphyrins in Catalytic Oxidation* (New York: Dekker)
- [2] Duke S O and Reberz C A (Eds) 1994 *Porphyrin Pesticides—Chemistry, Toxicology, and Pharmaceutical Applications*, (Washington DC: American Chemical Society)
- [3] Tang C W 1986 *Appl. Phys. Lett.* **48** 183
- [4] Nalwa H S 1993 *Adv. Mater.* **5** 341
- [5] Brédas J L, Adant C, Tackx P, Persoons A and Pierce B M 1994 *Chem. Rev.* **94** 243
- [6] Long N J 1995 *Angew. Chem. Int. Ed. Engl.* **34** 21
- [7] Nalwa H S and Miyata S (Eds) 1997 *Nonlinear Optical of Organic Molecules and Polymers* (Boca Raton, FL: Chemical Rubber Corp.) pp722–736
- [8] Fernández-Lázaro F, Torres T, Hauschel B and Hanack M 1998 *Chem. Rev.* **98** 563
- [9] de la Torre G, Vázquez P, Agulló-López F and Torres T 1998 *J. Mater. Chem.* **8** 1671
- [10] Shirk J S, Lindle J R, Bartoli F J and Boyle M E 1992 *J. Phys. Chem.* **96** 5847
- [11] Chen L X, Mandal B K, Bihari B, Sinha A K and Kamath M 1995 *SPIE Proc.* **61** 2527
- [12] Philip R, Ravikanth M and Kumar G R 1999 *Opt. Commun.* **165** 91
- [13] Nalwa H S, Hanack M, Pawlowski G and Engel M K 1999 *Chem. Phys.* **245** 17
- [14] Kuebler S M, Denning R G and Anderson H L 2000 *J. Am. Chem. Soc.* **122** 339
- [15] Unnikrishnan K P, Thomas J, Nampoori V P N and Valabhan C P G 2002 *Chem. Phys.* **279** 209
- [16] Daniels R B, Peterson J, Porter W C and Wilson Q D 1993 *J. Coord. Chem.* **30** 357
- [17] Wang X, Liu C, Gong Q, Huang Y and Huang C 2001 *Opt. Commun.* **197** 83
- [18] Wang X, Liu C, Gong Q, Huang Y, Huang C and Jiang J 2002 *Appl. Phys. A* **75** 497
- [19] Manas E S, Spano F C and Chen L X 1997 *J. Chem. Phys.* **107** 707
- [20] Huang W, Xiang H, Gong Q, Huang Y, Huang C and Jiang J 2003 *Chem. Phys. Lett.* **374** 639
- [21] Ng D K P and Jiang J 1997 *Chem. Soc. Rev.* **26** 433
- [22] Liu W, Jiang J, Pan N and Arnold D P 2000 *Inorg. Chim. Acta* **310** 140
- [23] Jiang J, Liu W, Law W and Ng D K P 1998 *Inorg. Chim. Acta* **268** 49
- [24] Jiang J, Arnold D P and Yu H 1999 *Polyheron* **18** 2129
- [25] Ishikawa N and Kaizu Y 1996 *J. Phys. Chem.* **100** 8722
- [26] Ricciardi G, Rosa A, van Gisbergen S J A and Baerends E J 2000 *J. Phys. Chem. A* **104** 635
- [27] Li J, Wang S, Yang H, Gong Q, An X, Chen H and Qiang D 1998 *Chem. Phys. Lett.* **288** 175
- [28] Gong Q, Li J, Zhang T and Yang H 1998 *Chin. Phys. Lett.* **15** 30
- [29] Wang S, Huang W, Liu C, Yang H, Gong Q, Kobayashi T, Takeyama T, Horikiri M and Miura Y 2003 *Chin. Phys.* **12** 305
- [30] Couris S, Koudoumas E, Dong F and Leach S 1996 *J. Phys. B* **29** 5033
- [31] Minoshima K, Jaiji M and Kobayashi T 1991 *Opt. Lett.* **16** 1683
- [32] Wang S, Huang W, Zhang T, Yang H, Gong Q, Horikiri M and Miura Y F 1999 *Appl. Phys. Lett.* **75** 1845
- [33] Shirk J S, Lindle J R, Bartoli F J, Kafafi Z H, Snow A W and Boyle M E 1992 *Int. J. Nonlinear Opt. Phys.* **1** 699
- [34] Nalwa H S and Kakuta A 1995 *Thin Solid Films* **254** 218